



Since 1994

► High Performance Polyaspartic



Sherwin Williams 80% Solids Polyaspartic

SUPREME & PREMIUM HIGH GLOSS TOPCOAT

- Chemical Resistant
- Ultraviolet Light Resistant
- Rapid Cure
- Low VOC's
- USDA, FDA, EPA, OSHA, and ADA Compliant



**SHERWIN
WILLIAMS**



SHERWIN-WILLIAMS®

CURED PHYSICAL PROPERTIES

60 Gloss	ASTM D523	90+
Impact Resistance	MIL D2794	>160
Adhesion	ASTM D4541	400 psi
Hardness/Shore D	ASTM 2240	70
Compression Strength	ASTM C579	18,000 psi
Tensile Strength	ASTM D638	3,000 psi
Abrasion Resistance, Taber Abrader CS-17 Wheel, 1000gm. load, 1000 cycles	ASTM D4060	15 mg loss
QUV	UVB-373/1500 hrs	90%
Flexibility (1/4 Cylindrical Mandrel)	ASTM D-1737	Pass
Coefficient of Friction	ASTM D-2047	>0.6



CHEMICAL RESISTANCE

Acetic Acid 100%	F
Acetone	F
Ammonium Hydroxide 50%	G
Benzene	F
Brine Saturated H2O	E
Chlorinated H2O	E
Clorox H2O	E
Diesel Fuel	G
Gasoline	G
Gasoline/5% MTBE	G
Gasoline/5% Methanol	G
Hydrochloric Acid 20%	E
Hydrofluoric Acid 10%	OS
Hydraulic Fluid (oil)	G
Isopropyl Alcohol	E
Lactic Acid	G
MEK	G
Methanol	E
Methylene Chloride	F
Mineral Spirits	G
Motor Oil	E
MTBE	F
Muriatic Acid 10%	E
NaCl/H2O 10%	E
Nitric Acid 20%	OS
Phosphoric Acid 10%	E
Phosphoric Acid 50%	OS
Potassium Hydroxide 10%	E
Potassium Hydroxide 20%	NR
Propylene Carbonate	G
Skydrol	F
Sodium Hydroxide 25%	E
Sodium Hydroxide 50%	NR
Sodium Hypochlorite 10%	E
Sodium Bicarbonate	E
Stearic Acid	E
Sugar/H2O	E
Sulfuric Acid 10%	E
Sulfuric Acid >50%	G
Toluene	E
1, 1, 1-Trichlorethane	F
Trisodium Phosphate	E
Vinegar/H2O 5%	E
H2O	E
H2O 14 Days at 82°C	G
Xylene	G

E = Excellent (Not Effected)
 G = Good (Limited Negative Effect)
 F = Fair (Moderate Negative Effect)
 OS = Occasional Spill
 NR = Not Recommended for this Chemical



We craft floors that perform brilliantly.